

# Primer K 200



for non-absorbent and painted plastic surfaces

For pre-treating non-absorbent and lacquered surfaces, plastic materials (ABS, rigid PVC, PA 6.6, FRP, SMC, PUR), metals (aluminium, steel, stainless steel, brass, zinc, tinplate) and elastomers (EPDM).

## Technical data

Basis	Synthetic resin, solvent-based
Colour	Uncoloured, transparent
Density	0.77 g/cm <sup>3</sup>
Consumption per m <sup>2</sup>	20 - 40 ml
Working temperature	+10 bis +35 °C
Evaporation time after application	ca. 10 min.
Adhesive application at the latest after	24 hours

Suitable for:

- WEICON Urethane
- WEICON Easy-Mix PU 90 und PU 240
- WEICON 1-Component Adhesives and Sealants (except Silicones)

## Pretreatment of the surface

The surfaces to be treated must be dry, clean, and free of dust and grease (e.g. WEICON Surface Cleaner).

## Processing

Shake well before use, then apply a thin layer with a clean cloth.

Recommended evaporation time:

- Primer M 100: minimum 10 minutes, max. 24 hours
- Primer K 200: minimum 10 minutes, max. 24 hours
- Primer S 300: minimum 60 minutes, max. 4 hours
- Primer P 400: minimum 10 minutes, max. 1 hour
- Primer E 500: minimum 60 minutes, max. 8 hours

The following bonding process should be done within the time period mentioned above. Please respect the minimum evaporation time. After a longer storage time or soiling in the meantime, clean again the bonding surfaces and apply again the primer. For unknown material types it is necessary to test suitability and compatibility.

## Storage

Keep away from sources of ignition - No smoking. The heavy vapours may bridge a long distance to source of ignition.

Vapours can form an explosive mixture with air. Highly volatile, flammable components are released in processing. Take precautionary measures against static discharges. Prevent penetration into the ground. Do not store together with food.

Store closed container at cool and aired place. Protect from heat and direct solar radiation. Store in a dry place. Protect from heat/overheating.

When unopened and stored in a normal climate (+23°C and 50 % rel. humidity), WEICON Primer have a shelf life of 9 - 12 months, depending on the type.

## Note

Any product specifications and recommendations given herein must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do warrant the continuously high quality of our products being free from defects in accordance with and subject to our General Sales Conditions. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

## Health and Safety

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

### WEICON GmbH & Co. KG (Headquarter)

Königsberger Str. 255 · DE-48157 Münster  
P.O. Box 84 60 · DE-48045 Münster  
Germany

Tel. +49 (0) 251 / 93 22-0  
Fax +49 (0) 251 / 93 22-244  
Fax +49 (0) 251 / 93 22-233 Export  
[www.weicon.de](http://www.weicon.de) · [info@weicon.de](mailto:info@weicon.de)

### WEICON Middle East L.L.C.

Jebel Ali Ind Area 3 · P.O. Box 118 216  
Dubai · U.A.E

Phone +971 4 880 25 05  
Fax +971 4 880 25 09  
Mobile +971 50 545 99 83  
[www.weicon.ae](http://www.weicon.ae) · [info@weicon.ae](mailto:info@weicon.ae)

### WEICON Inc.

20 Steckle Place · Unit 20  
Kitchener · Ontario · N2E 2C3  
Canada

Phone +1 519 896 5252  
Fax +1 519 896 5254  
Cell +1 519 590 5168  
[www.weicon.ca](http://www.weicon.ca) · [info@weicon.ca](mailto:info@weicon.ca)

### WEICON Kimya Sanayi Tic. Ltd. Şti.

Yenibosna Mahallesi Yalçın Koreş Caddesi  
Arifağa Sokak No: 29 Kat: 3  
34530 Yenibosna – İstanbul Turkey  
[www.weicon.biz.tr](http://www.weicon.biz.tr) · [info@weicon.biz.tr](mailto:info@weicon.biz.tr)

### WEICON Romania SRL

Str. Podului Nr.1  
547176 Budiu Mic (Targu Mures)  
[www.weicon.com](http://www.weicon.com) · [office@weicon.com](mailto:office@weicon.com)